



KISUMA CHEMICALS BV  
Billitonweg 7  
9641 KZ Veendam  
P.O. Box 400  
9640 AK Veendam  
The Netherlands

Tel. +31 598 666 766  
Fax. +31 598 690 792  
support@kisuma.com

# KISUMA CHEMICALS DATASHEET

## ALCAMIZER PLUS

### Mg-Al Hydrotalcite as heat stabilizer in heavy metal free PVC stabilizer systems

#### Features:

Suitable for all resins. High heat stability combined with high transparency and no deterioration of the insulating characteristics of PVC. High volume of compounding and good dispersion characteristics. No sulfide pollution. Good weatherability and high personal safety.

#### Specified and Typical Properties:

	Typical value	General specification	
Appearance	Free flowing White powder	-	
Molar ratio MgO/Al <sub>2</sub> O <sub>3</sub>	4.2	min 3.7 max 4.6	
Loss on Drying (105C 1 hr)	0.2	max 0.5	w/w%
Specific Surface Area	10	min 5 max 20	m <sup>2</sup> /g
Secondary particle size Average	0.5	min 0.3 max 0.8	µm
> 5 µm		0	µm vol %
Specific Gravity	2.1	-	
Mohs hardness	2.0	-	
Refractive index	1.50	-	
Temp. of commencing dehydration	185	-	°C
Amount of linseed oil absorbed	50	-	ml/100g