



KISUMA CHEMICALS BV Tel. +31 598 666 766
Billitonweg 7 Fax. +31 598 690 792
9641 KZ Veendam
P.O. Box 400 support@kisuma.com
9640 AK Veendam
The Netherlands

KISUMA CHEMICALS DATASHEET

ALCAMIZER P93

Mg-Al-Zn Hydrotalcite as heat stabilizer in heavy metal free PVC stabilizer systems

Features:

Suitable for all resins. High heat stability combined with high transparency and no deterioration of the insulating characteristics of PVC. High volume of compounding and good dispersion characteristics. No sulfide pollution. Good weatherability and high personal safety.

Specified and Typical Properties:

	Typical value	General specification	
Appearance	Free flowing White powder	-	
Molar ratio MgO/Al ₂ O ₃	3	min 2.8 max 3.2	
Molar ratio ZnO/Al ₂ O ₃	1	min 0.8 max 1.2	
Loss on Drying (105°C/1hr)	0.2	max 0.5	w/w%
Specific Surface Area	7	min 5 max 10	m ² /g
Secondary particle size Average	0.7	min 0.6 max 0.9	µm
> 5 µm		0	µm vol %
Specific Gravity	2.3	-	
Mohs hardness	2.0	-	
Refractive index	1.54	-	
Temp. of commencing dehydration	185	-	°c
Amount of linseed oil absorbed	50	-	ml/100g